DATE / FECHA: **JUNE 10TH 2011 /** *Junio 10 de 2011*

COMMERCIAL SPECIFICATION / *ESPECIFICACIÓN COMERCIAL*

NAME / NOMBRE: VALENCIA-A

PRODUCT LINES / *LINEA DE PRODUCTOS*		
CATEGORY / *CATEGORÍA*		Contract & Home / *Institucional y Residencial*
SEGMENT / *SEGMENTO*		Contract Quality / *Institucional*
SUBSEGMENT / *SUBSEGMENTO*		Upholstery / *Tapicería*
GENERAL / *GENERAL*		
TOTAL WEIGHT / *PESO TOTAL* -g/m^2 - ASTM D-751		640 ± 65
WIDTH / *ANCHO* - m - ASTM D-751		Min. 1.37
GAUGE / *CALIBRE* - mm - DIN 53353		1.10 ± 0.16
EMBOSSING / *GRABADO*		M 2
PRINT / *ESTAMPADO*		-
SUBSTRATE / *BASE*		
TYPE / *TIPO*		Polyester / *Poliéster*
DESCRIPTION / *DESCRIPCION*		
WEIGHT / *PESO* - g/m^2		130
MISCELLANEOUS / *VARIOS*		
ANTI-BACTERIAL / *ANTIBACTERIAL*		-
BACTERIAL RESISTANCE / *RESISTENCIA A BACTERIAS* (AATCC TM 147)		Passes / *Pasa*
MILDEW RESISTANCE / *RESISTENCIA A HONGOS* (ASTM G21)		No Growth (NG) / *SIn Crecimiento*
ANTI-STATIC / *ANTIESTÁTICO* - ASTM D-257		Passes / *Pasa*
PINK STAIN (ASTM E-1428) *		-
SULFIDE STAINING / *MANCHADO POR AZUFRE* (FISHER BODY TM 31-12)		-
INK STAIN RESISTANCE / *RESISTENCIA AL MANCHADO POR TINTA* (PLTM 1120		-
TOPCOAT / *LACA*		-
FLAME RETARDANCY / *RETARDANCIA AL FUEGO*		
FMVSS 302		Passes / *Pasa*
BOSTON FIRE CODE - BFD 1X-1		-
IMO A.652 (16) 8.2 and 8.3		Passes / *Pasa*
FEDERAL ST. 191A M 5903.1		Passes / *Pasa*
FAR 25.853 b(4) Appendix F Part. I (a) (1) (ii)		Passes / *Pasa*
UNE 23.727 90		M 2
EN/ BS/ DIN/ 1021 PARTE 1 & 2		Passes / *Pasa*
DIN 4102 B2		-
DIN 53438		-
DIN 75200		-
ÖNORM B 3258		-
ÖNORM B 3800 Teil 1		-
CALIFORNIA TECH. BULLETIN 117 - Section E		Passes / *Pasa*
BIFMA X5.7 - Fabric Class - Class A		Passes / *Pasa*
BIFMA X5.7 - Fabric Screening - Class I		Passes / *Pasa*
UFAC Fabric - Class I		Passes / *Pasa*
NFPA 260 - Cover Fabric - Class I		Passes / *Pasa*
NATIONAL SCHOOL BUS SEAT UPHOLSTERY - Fire Block Test		-
NY/NJ PORT OF AUTHORITY		-
CALIFORNIA TECH. BULLETIN 133 - Part 1-2		-
BS 5852 Part 2 Crib 5 - UNITED KINGDOM		-
NFP 92503 - M3		-
MASS. 527 CMR 21.00		-
AS1530 - AUSTRALIA		-
		-
		-
		-
		-
		-
TENSILE STRENGTH / *RESISTENCIA A LA TENSION* **ASTM D-751**		
Kgf (MIN.)	Warp / *Urdimbre*	55
	Fill / *Trama*	33
ELONGATION AT BREAK / *ELONGACION A RUPTURA* **ASTM D-751**		
% (AVE.)	Warp / *Urdimbre*	67
	Fill / *Trama*	159
TEAR STRENGTH - TRAPEZOID METHOD / *RESISTENCIA AL RASGADO* **- ASTM D-751**		
Kgf (MIN.)	Warp / *Urdimbre*	8.0
	Fill / *Trama*	8.3
STITCHING STRENGTH / *RESISTENCIA A LA PUNTADA* **- DIN 54301**		
Kgf (MIN.)	Warp / *Urdimbre*	5.7
	Fill / *Trama*	3.9
ADHESION / *ADHESION* **- ASTM D-751**		
Kgf / pulg (MIN.)	Warp / *Urdimbre*	1.5
	Fill / *Trama*	1.5
ABRASION / *ABRASION* **- UNE EN ISO 12947**		
ABRASION MARTINDALE		> 300,000 Cycles / *Ciclos*
ACCELERATED LIGHT AGING / *SOLIDEZ A LA LUZ*		
XENOTEST: AATCC TM 16-3/ NTC 1479/ CFFA-2 a1 - Blue Wool / *Lana Azul*		Cal≥7 1,000 hours = Passes / *Pasa*
QUV: ASTM D-4329/ CFFA-2 c2 - Grey Scale / *Escala de Grises* ISO 105-B02		-
CROCKING / *SOLIDEZ AL ROCE* **- CFFA 7 / FED ST. 191A M 5651**		
WET/DRY / *HUMEDO/SECO*		Excellent / *Excelente*
COLD CRACK / *RESISTENCIA A BAJAS TEMPERATURAS* **- CFFA 6a**		
ROLLER METHOD		Passes / *Pasa* -23 ℃
PINHOLES / SQUARE INCH		
UNITS		-
STRETCH - SAE J 855		
% (AVERAGE)	Warp / *Urdimbre*	-
	Fill / *Trama*	-
SET - SAE J 855		
% (AVERAGE)	Warp / *Urdimbre*	-
	Fill / *Trama*	-
BLOCKING / *BLOCKING*		
CFFA-4		-
		-
		-

Note. The data correspond to minimum results of the statistical analysis. The information included in this specification is subject to

THE INDICATED DATA CORRESPONDING TO THE MATERIAL'S PHYSICAL CHARACTERISTICS ARE RESULTS OF TESTS CONDUCTED UNDER STANDARD PROCEDURES AND ARE SUBJECT TO VARIATIONS. THEREFORE DOCUMENTS OUR SUPPLIERS TO EVALUATE THE MATERIAL THEY REQUIRE FOR TO THEIR SPECIFIC REQUIREMENTS AND THESE TERMS AND ANY CORRESPONDING DATA REFER TO THE TYPICAL PERFORMANCE IN THE SPECIFIC TESTS INDICATED AND SHOULD NOT BE CONSTRUED TO IMPLY THE REALIZATION OF THIS OR ANY OTHER MATERIAL UNDER A TRUE CONTRACT. PROQUINAL S. A. DOES NOT ASSUME ANY RESPONSIBILITY FOR ANY DAMAGES RESULTING FROM INADEQUATE USES, DIFFERENT TO THOSE MENTIONED IN THIS PROCEDURE AND ANY OTHER DAMAGES RESULTING FROM THE USE OF THE MATERIAL IN ACCORDANCE WITH THIS PROCEDURE. PROQUINAL S. A. DOES NOT GUARANTEE EXACT COLOR MATCHES AS SLIGHT VARIATIONS IN PRODUCTION AND STOCK MAY OCCUR. FOR THIS REASON WE DO NOT PROMOTE COLOR MATCHES OF DIFFERENT FABRICATION SITES. PROQUINAL S. A. RESERVES THE RIGHT TO MODIFY TECHNICAL SHEETS WITHOUT PREVIOUS WARNING. / PROQUINAL S. A. SE RESERVA EL DERECHO DE CAMBIAR LA ESPECIFICACIÓN SIN PREVIO AVISO.

I-LAB-020 Revisión No. 02